

DESCRIPTION OF THE PRODUCT

Water-based transparent low dust-grip transparent protective coating, formulated by WINKLER's research & development Laboratories.

USE FIELD

The product should be applied on protective/waterproofing reflective products of WINKLER's range. Associated with recurrent cleaning, it assures a longer duration of reflective characteristics of the underneath products.

SURFACE PREPARATION

Accurately clean the support and eliminate possible water condensation. Protective / waterproofing products must have undergone at least 48-72 hours of curing, after last coat application, before applying WINCLEAN.

WARNING

Do not add any additive.

Do not use the packaging if damaged.

Do not add water or solvents.

Protect the product during the first 24 hours from water, rain, snow. Do not apply if night humidity is high. Apply at temperatures between +5°C and +35°C.

APPLICATION

The product is ready to use and can be applied on clean and dry support by roller, brush, and spraying airless gun.

CONSUMPTION

80 g/m² in one coat.

PACKAGING

5-20ltrs jerrycans

STORAGE

The product in its undamaged packaging can be stored for 12 months. Please store it at temperatures between +5°C and +35°C. (No frost-proof).

SAFETY INSTRUCTIONS

PRECAUTIONS

For information about safety, user must refer to the most recent Safety Data Sheet, edited in accordance with the regulations in force, which contains physical, toxic and other data about the product in use.

ECOLOGY

Do not dispose the product and/or empty containers in the environment. Consult the most recent Safety Data Sheet for further information about disposals.

TECHNICAL FEATURES

FEATURES	STANDARD	RESULTS
Look	-	Liquid
Colour	-	Milky
Colour after complete dry	-	Transparent
Out of dust 20°C	-	1 hour
Density at 20°C	EN ISO 2811-1	1.02 ± 0.05 g/cm ³
Solid content	EN ISO 3251	15 ± 2%
PH	UNI 8490-4	8.5 ± 1
Brookfield viscosity at 20°C:	UNI EN 8490	15 ± 1 cps

PRODUCT FOR PROFESSIONALS

The information contained in this technical data sheet is to the best of our knowledge correct. However, by no means can it be considered a guarantee, as usage, working area and application of the product in accordance with the instructions given and their success in application is beyond our control and is dependent on a number of factors. We decline any responsibility for the improper use of the product as the application recommendations contained herein are to be considered as a general guideline. If at all in doubt, preliminary tests should be carried out. WINKLER S.r.l. reserves the right to modify and up-date said data sheets without prior notice. Clients are kindly requested to verify that they are in possession of the current edition.